

COLLATION SHRINK

FIELD OF THE INVENTION

[0001] The invention relates to co-extruded structures for collation shrink films and blends of polyethylene used therefor.

BACKGROUND OF THE INVENTION

[0002] Collation shrink concerns the bundling of items together using heat shrinkable film. Collation shrink is used for a very wide variety of applications and notably for the secondary packaging of food or drinks. Examples include metal cans and plastic bottles.

[0003] Typically, films are applied at room temperature and placed under a heat source to shrink. Suitable performance characteristics on the shrink packaging line include sufficient stiffness allowing the film to be correctly wrapped around the items being packaged, sufficient dimensional shrinkage to ensure a snug fit, and a low enough Coefficient of Friction (COF). Films appropriate for use as collation shrink must have a high thermal shrink force to ensure a tight fit and high tensile strength to withstand handling and abuse during transportation.

[0004] In addition, the packaging must have excellent display properties including gloss (preferably under different angles to maximize appeal), haze (or "contact clarity") and clarity ("see-through clarity").

[0005] Finally, the collation shrink film manufacturer wants the properties of a low melt pressure, and the ability to use low motor power, both allowing higher production rates.

[0006] While it is known how to improve many of the above properties individually, currently available structures do not combine all of the properties satisfactorily in a film having sufficiently thin gauge to be commercially attractive.

[0007] Polyethylene is an attractive component to use in collation shrink film. Various types of polyethylenes are known in the art. Low density polyethylene ("LDPE") can be prepared at high pressure using free radical initiators and typically has a density in the range of 0.916-0.940 g/cm³. LDPE is also known as

"branched" or "heterogeneously branched" polyethylene because of the relatively large number of long chain branches extending from the main polymer backbone. Polyethylene in the same density range, i.e., 0.916 to 0.940 g/cm³, which is linear and does not contain large quantities of long chain branching is also known; this "linear low density polyethylene" ("LLDPE") can be produced with conventional Ziegler-Natta catalysts or with metallocene catalysts. Relatively higher density LDPE or LLDPE, typically in the range of 0.928 to 0.940g/cm³ are sometimes referred to as medium density polyethylene ("MDPE") or Linear Medium Density Polyethylene (MDPE). Polyethylenes having still greater density are the high density polyethylenes ("HDPEs"), i.e., polyethylenes having densities greater than 0.940 g/cm³, and are generally prepared with Ziegler-Natta catalysts, chrome catalysts or even metallocene catalysts. Very low density polyethylene ("VLDPE") is also known. VLDPEs can be produced by a number of different processes yielding polymers with different properties, but can be generally described as polyethylenes having a density less than 0.916 g/cm³, typically 0.890 to 0.915 g/cm³ or 0.900 to 0.915 g/cm³.

[0008] U.S. Pat. No. 6,187,397 teaches a 3-layer co-extruded heat-shrinkable film devoid of metallocene polyethylene. The patent teaches that prior art "high clarity" heat-shrinkable polyethylene films are obtained by coextrusion of three layers comprising a central layer of predominantly (>50 wt.%) free-radical polyethylene having a relative density of 0.918-0.930, optionally with HDPE to confer stiffness, sandwiched between two layers of predominantly (80-90 wt.%) metallocene linear polyethylene having a density of 0.918-0.927.

[0009] U.S. Pat. No. 6,340,532 discloses shrink films manufactured from "pseudohomogeneous" linear low density polyethylene resins preferably prepared with an advanced Ziegler Natta catalyst. Various deficiencies of "homogeneous" resins, i.e., metallocene resins, used in prior art shrink films are discussed.

[0010] U.S. Pat. No. 6,368,545 teaches a high clarity multilayer blown coextruded film prepared using special methods, wherein a film is described having a central core of HDPE.

[0011] U.S. Pat. Application No. 20020187360 is directed to a heat shrinkable, co-extruded polyethylene film laminate having a relatively low melting point core

layer comprising a linear low density polyethylene (LLDPE) having a density of 0.910-0.930 g/cm³ and a linear very low density polyethylene (VLDPE) having a density of 0.880-0.915 g/cm³, sandwiched between two relatively higher melting point surface layers comprising a linear low density polyethylene and a linear high density polyethylene.

[0012] WO 01/44365 describes a homogeneous blend of a metallocene-catalyzed medium density polyethylene (mMDPE) with a low density polyethylene (LDPE) to produce blown films. The blend may be coextruded between layers of LDPE to make blown films taught in the reference as having the good optical properties of LDPE and the good mechanical and processing properties of MDPE.

[0013] The high gloss provided by metallocene polyethylenes is a very attractive property. However, film layers comprising metallocene polyethylene have a very high coefficient of friction in the absence of specific additives. These additives, in turn, detract from the optical properties desired in collation shrink films. A film exploiting the high gloss capabilities of metallocene polyethylene that can be produced efficiently and having the properties sought in a collation shrink film is highly desirable.

[0014] The present inventor has surprisingly discovered that an improved collation shrink film may be achieved by a structure having a core layer comprising HDPE and skin layers comprising metallocene polyethylene and optionally HDPE.

SUMMARY OF THE INVENTION

[0015] The invention is directed to a film structure having at least two layers: a layer comprising HDPE and layer comprising a metallocene-catalyzed polyethylene (hereinafter mPE), optionally further comprising HDPE. The invention is further directed to a collation shrink-wrapped structure comprising the aforementioned film shrink wrapped around various items.

[0016] In a preferred embodiment the film structure comprises a core layer comprising HDPE sandwiched by two metallocene skin layers. In a more preferred embodiment at least one of said metallocene skin layers further comprises HDPE.

[0017] It is an object of the present invention to provide various embodiments of the aforementioned inventions having unique properties, particularly with respect to optical, strength, and processing properties, as well as performance in the resultant shrink-wrapped structure.

[0018] Another object of the present invention is to provide a collation shrink film having suitable performance on the shrink packaging line.

[0019] Still another object of the present invention to provide a shrink collation film having appropriate properties to handle abuse during transportation.

[0020] Yet another object of the present invention to provide shrink wrapped structure having attractive display properties at the point of sale.

[0021] These and other objects, features, and advantages will become apparent as reference is made to the following detailed description, preferred embodiments, examples, and appended claims.

DETAILED DESCRIPTION

[0022] In an embodiment, a film structure is provided having at least two layers. One layer comprises a high density polyethylene (hereinafter "HDPE") and the second layer comprises a mPE.

[0023] As used herein, HDPE means polyethylene having a density of greater than 0.940 g/cm^3 . The terms "high density polyethylene" polymer and "HDPE" polymer refer to a homopolymer or copolymer of ethylene having a density greater than 0.940 g/cm^3 . Polymers having more than two types of monomers, such as terpolymers, are also included within the term "copolymer" as used herein.

[0024] The comonomers that are useful in general for making HDPE copolymers useful in the present invention include α -olefins, such as C_3 - C_{20} α -olefin and preferably C_3 - C_{12} α -olefins. The α -olefin comonomer can be linear or branched, and two or more comonomers can be used, if desired. Examples of suitable comonomers include linear C_3 - C_{12} α -olefins, and α -olefins having one or more C_1 - C_3 alkyl branches, or an aryl group. Specific examples include propylene; 3-methyl-1-butene; 3,3-dimethyl-1-butene; 1-pentene; 1-butene; 1-pentene with one or more methyl, ethyl or propyl substituents; 1-hexene; 1-hexene with one or more methyl, ethyl or propyl substituents; 1-heptene with one or more

methyl, ethyl or propyl substituents; 1-diecene; 1-dodecene; 1-octene with one or more methyl, ethyl or propyl substituents; 1 -nonene with one or more methyl, ethyl or propyl substituents; ethyl, methyl or dimethyl-substituted 1-decene; 1-dodecene; and styrene. It should be appreciated that the list of comonomers above is merely exemplary, and is not intended to be limiting.

[0025] Preferred comonomers include propylene, 1-butene, 1-pentene, 4-methyl-1-pentene, 1-hexene, 1-octene and styrene. Other useful comonomers include polar vinyl, conjugated and non-conjugated dienes, acetylene and aldehyde monomers, which can be included in minor amounts in terpolymer compositions. Non-conjugated dienes useful as co-monomers preferably are straight chain, hydrocarbon di-olefins or cycloalkenyl-substituted alkenes, having 6 to 15 carbon atoms. Suitable non-conjugated dienes include, for example: (a) straight chain acyclic dienes, such as 1,4-hexadiene and 1,6-octadiene; (b) branched chain acyclic dienes, such as 5-methyl-1,4-hexadiene; 3,7-dimethyl-1,6-octadiene; and 3,7-dimethyl-1,7-octadiene; (c) single ring alicyclic dienes, such as 1,4-cyclohexadiene; 1,5-cyclo-octadiene and 1,7-cyclododecadiene; (d) multi-ring alicyclic fused and bridged ring dienes, such as tetrahydroindene; norbornadiene; methyl-tetrahydroindene; dicyclopentadiene (DCPD); bicyclo-(2.2.1)-hepta2,5-diene; alkenyl, alkylidene, cycloalkenyl and cycloalkylidene norbornenes, such as 5-methylene-2-norbornene (NINB), 5-propenyl-2-norbornene, 5-isopropylidene-2-norbornene, 5-(4-cyclopentenyl)-2-norbornene, 5-cyclohexylidene-2-norbornene, and 5-vinyl-2-norbornene (VNB); and (e) cycloalkenyl-substituted alkenes, such as vinyl cyclohexene, allyl cyclohexene, vinyl cyclooctene, 4-vinyl cyclohexene, allyl cyclodecene, and vinyl cyclododecene. Of the non-conjugated dienes typically used, the preferred dienes are dicyclopentadiene, 1,4-hexadiene, 5-methylene-2-norbornene, and 5-ethylidene-2-norbornene. Particularly preferred diolefins, are 5-ethylidene-2-norbornene (ENB), 1,4-hexadiene, dicyclopentadiene (DCPD), norbornadiene, and 5-vinyl-2norbornene (VNB).

[0026] The amount of comonomer used will depend upon the desired density of the HDPE polymer and the specific comonomers selected. One skilled in the art can readily determine the appropriate comonomer content appropriate to produce an HDPE polymer having a desired density.

[0027] In one embodiment, the HDPE polymer has a density of greater than 0.940 g/cm³, preferably from about 0.940 g/cm³ to about 0.970 g/cm³, more preferably from about 0.955 g/cm³ to about 0.965 g/cm³, and most preferably from about 0.960 g/cm³ to about 0.965 g/cm³. Densities referred to herein are in accordance with ASTM D 1505.

[0028] In one embodiment, the HDPE polymer may have a melt index from 0.01 to 45 g/10 min, as measured in accordance with ASTM-1238 condition E. The HDPE polymer may be produced using any conventional polymerization process, such as a solution, a slurry, or a gas-phase process, and a suitable catalyst, such as a chrome catalyst, a Ziegler-Natta catalyst or a metallocene catalyst. It is preferred that the HDPEs used in the blends according to the present invention be produced using Ziegler-Natta catalysts.

[0029] Examples of suitable HDPE useful in the present invention include HDPEs available from ExxonMobil Chemical Co., Houston, Texas, under the HD, HDA, HMA, HRA, HRP, HDZ or HYA series or under the trademark PAXON. Preferred examples of HDPE include HYA800, produced in the gas phase, and HDZ222, produced by the stirred slurry process. Blends of two or more HDPE polymers and one or more HDPE polymers with one or more non-HDPE polymers are also contemplated.

[0030] The HDPE component of the first layer should be present in the amount of between about 1 wt.% and 50 wt.%, preferably between about 10 wt.% and 50 wt.%, more preferably between about 15 wt.% and 45 wt.%. This first layer should also comprise from between about 99 wt.% and 50 wt.% LDPE, preferably between about 90 wt.% and 50 wt.%, more preferably between about 85 wt.% and 55 wt.%. In a preferred embodiment the first layer can also comprise LLDPE (e.g., a tri-blend).

[0031] The LDPE suitable for use in the present invention is free-radical initiated LDPE having a density in the range of 0.916 to 0.940 g/cm³, preferably 0.924 to 0.940 g/cm³. In an embodiment, the LDPE blended with the HDPE in this layer has a density in the range of 0.916 to 0.935 g/cm³, more preferably 0.926 to 0.935 g/cm³. In another embodiment, the LDPE blended with the HDPE in this layer has a density in the range of 0.916 to 0.927 g/cm³, and more preferably 0.921 to

0.926 g/cm³. Preferred specific LDPEs are LD170BA and experimental grades EX489BA and EX514BA, also available from ExxonMobil Chemical Co., Houston, TX.

[0032] Additional polyolefins may be added, such as VLDPE, provided that the aforementioned wt.% of HDPE and LDPE is met. Likewise, the blend of HDPE and LDPE may include various additives, as discussed in more detail below. However, it is preferred that the blend of HDPE and LDPE comprising the first layer of the film structure does not contain slip or antiblock additives. In a preferred embodiment, this layer contains no metallocene polyethylene. In another embodiment, mPE may be added, particularly in the case where additional toughness is required.

[0033] The second layer of the film structure according to the present invention comprises a metallocene polyethylene (mPE). In a preferred embodiment, the mPE is a linear low density polyethylene (hereinafter "mLLDPE"). In another preferred embodiment the mPE is a VLDPE (hereinafter "mVLDPE") having a density of between about 0.910 to 0.915 g/cm³. In the case where the HDPE component of the blend is also a metallocene polyethylene, the second component of the invention must be a mLLDPE or the aforementioned mVLDPE.

[0034] A "metallocene polyethylene" as used herein means a polyethylene produced by a metallocene catalyst. As used herein, the term "metallocene catalyst" is defined to be at least one metallocene catalyst component containing one or more substituted or unsubstituted cyclopentadienyl moiety (Cp) in combination with a Group 4, 5, or 6 transition metal (M).

[0035] The metallocene catalyst precursors generally require activation with a suitable co-catalyst, or activator, in order to yield an "active metallocene catalyst", i.e., an organometallic complex with a vacant coordination site that can coordinate, insert, and polymerize olefins. The active catalyst systems generally includes not only the metallocene complex, but also an activator, such as an alumoxane or a derivative thereof (preferably MAO), an ionizing activator, a Lewis acid, or a combination thereof. Alkylalumoxanes are additionally suitable as catalyst activators. The catalyst system is preferably supported on a carrier,

typically an inorganic oxide or chloride or a resinous material such as polyethylene.

[0036] The prior art is replete with examples of metallocene catalysts/systems for producing polyethylene. Non-limiting examples of metallocene catalysts and catalyst systems useful in practicing the present invention include WO 96/11961; WO 96/11960; U.S. Pat. Nos. 4,808,561; 5,017,714; 5,055,438; 5,064,802; 5,124,418; 5,153,157; 5,324,800; more recent examples are U.S. Pat. Nos. 6,380,122; and 6,376,410; and WO01/98409, and references cited therein.

[0037] Particularly useful mPE suitable for the present invention include metallocene LLDPE (mLLDPE) under the Exceed trademark, available from ExxonMobil Chemical Company, Houston, TX. Particularly preferred is Exceed™ 1327CA polyethylene and Exceed™ 1018CA polyethylene, both commercially available mLLDPEs with a C₆ comonomer incorporated therein and produced in the gas phase.

[0038] In an embodiment, a blend suitable for the second layer of the film structure should comprise from between about 100 wt.% and 50 wt.% of mPE. Preferably the mPE has a density range of from 0.910 to 0.940 g/cm³ and more preferably 0.915 to 0.940 g/cm³. Optional components, in the amount of no more than 50 wt. %, include LDPE and/or HDPE. These are preferably selected from the commercially available or known LDPEs or HDPEs discussed herein. In another preferred embodiment, LDPEs suitable for use in this second layer are free-radical initiated LDPEs having a density in the range of 0.916 to 0.940 g/cm³, preferably 0.924 to 0.940 g/cm³. In an embodiment, the LDPE blended with the HDPE in this layer has a density in the range of 0.916 to 0.940 g/cm³, more preferably 0.921 to 0.935 g/cm³. In another embodiment, the LDPE blended with the HDPE in this layer has a density in the range of 0.916 to 0.927 g/cm³, and more preferably 0.921 to 0.926 g/cm³. Again, preferred specific examples of LDPEs are LD170BA and experimental grades EX489BA and EX514BA, mentioned above. Blends of two or more LDPEs are contemplated. The LDPE used in this second layer, if at all, may be the same or different as the LDPE used in the first layer.

[0039] Particularly preferred HDPE in this second layer include HDPEs available from ExxonMobil Chemical Co., Houston, Texas, under the HD, HDA, HMA, HRA, HRP, HDZ or HYA series or under the trademark PAXON, particularly HYA800 and HDZ222, discussed above. Blends of two or more HDPE polymers in this layer are also contemplated.

[0040] In the case where HDPE is present in the second layer, it may be the same or different than the HDPE in the first layer. Thus, the HDPE polymer has a density of greater than 0.940 g/cm^3 . In a preferred embodiment the HDPE in this layer has a density of from about 0.940 g/cm^3 to about 0.970 g/cm^3 , more preferably from about 0.955 g/cm^3 to about 0.965 g/cm^3 , and most preferably from about 0.960 g/cm^3 to about 0.965 g/cm^3 . This second layer may include various additives, as discussed in more detail below. However, it is preferred that this second layer, comprising mPE and optionally HDPE and/or LDPE, does not contain slip or antiblock additives.

[0041] Multilayer film forming techniques are well-known to one of ordinary skill in the art and the prior art is replete with examples; see, for instance, WO01/98409. Any of these techniques may be used to form multilayer films according to the present invention, but coextrusion is most preferred and provides the greatest advantage of the invention as regards collation shrink film structures.

[0042] While those of skill in the art will appreciate that the thickness of layers may be adjusted based on the desired end use, one of the surprising aspects of the present invention is that the composition of the layers of the present invention provide for multilayer films having the appropriate properties for collation shrink while being of sufficiently thin gauge to be commercially attractive.

[0043] Thus, according to one embodiment of the invention, the first layer comprising HDPE, as described above, and the second layer comprising mPE, is coextruded to form a multilayer film useful as collation shrink film. In the preferred collation shrink wrapped structure the second layer comprising the metallocene polyethylene is the outside layer with the first layer comprising HDPE in contact with the items shrink-wrapped.

[0044] In an embodiment the film according to the invention consists essentially of the first layer comprising HDPE and the second layer comprising mPE. In a

more preferred embodiment, the first layer is about 30 microns thick and the second layer is about 5 microns thick.

[0045] In another embodiment, the first layer comprising HDPE, described above, is a core layer between two skin layers, at least one of which is the second layer, comprising mPE, described above. The two skin layers may be the same or different, provided that at least one is a second layer, as described above, comprising mPE. In this embodiment, it is preferred that both skin layers also comprise mPE.

[0046] As used herein, the term "skin layer" means that the layer is the outer layer of the structure. Thus, a three-layer structure there are two skin layers and a core layer, sandwiched by the skin layers. This structure will be denoted A/B/A, wherein the A layer denotes a skin layer, corresponding to the second layer comprising mPE, above, and the B layer denotes the core layer, corresponding to the first layer described above. It will be recognized that the A layers do not need to be identical, however.

[0047] In still another embodiment, the structure includes a layer comprising HDPE without a metallocene polyethylene component, and a layer comprising a blend comprising metallocene polyethylene and HDPE. Optionally, the layer comprising HDPE without a metallocene polyethylene component is sandwiched between two skin layers comprising mLLDPE wherein at least one of the skin layers further comprises HDPE. The skin layers in any of these "skin and core" (or A/B/A) embodiments may be the same or different.

[0048] Additional film layers are contemplated, e.g., between one or both of A/B, e.g. as tie-layers. However, in the preferred embodiment the core layer B comprises HDPE and the skin layers A comprise mPE (i.e., corresponding to one of the first layers and two of the second layers, respectively, described above). The final film comprising the A/B/A structure may be symmetrical or it may be unsymmetrical.

[0049] In a more preferred embodiment the film according to the present invention comprises the A/B/A structure, wherein the A skin layers, which may be the same or different, each independently comprise an mPE having a density of between about 0.910 to 0.940 g/cm³, preferably 0.915 to 0.940 g/cm³, and

optionally an HDPE, preferably having a density of between about 0.940 and 0.970 g/cm³, more preferably 0.955 to about 0.965 g/cm³, and most preferably from about 0.960 to about 0.965 g/cm³, and the B core layer comprises an HDPE, preferably having a density of between about 0.940 and 0.970 g/cm³, more preferably 0.955 to about 0.965 g/cm³, and most preferably from about 0.960 to about 0.965 g/cm³, and an LDPE, preferably having a density in the range of 0.916 to 0.935 g/cm³, more preferably 0.921 to 0.930 g/cm³. In the case where there is HDPE in one or both of the skin layers, the HDPE in each layer is independently selected and it may be the same or different from the other layer and/or the core layer.

[0050] In this preferred A/B/A structure, it is more preferred that the core layer B comprise 60-90 wt.%, more preferably 70-80 wt.% LDPE, and 40-10 wt.% HDPE, more preferably 30-20 wt.%, and that the skin layers A are each independently selected from 80-100 wt.%, preferably 85-95 wt.% mPE, and 20-0 wt.% HDPE, more preferably 15-5 wt.%. In a preferred embodiment the A/B/A structure is symmetrical with respect to composition and thickness. In another preferred embodiment the A/B/A structure is no thicker than 50 microns and more preferably about 40 microns thick or less.

[0051] In a preferred embodiment, one or more of the layers of the multilayer film structure according to the invention may have certain additives, such as thermal stabilizers, but in this preferred embodiment each of the compositions of the various layers should specifically exclude slip or antiblock additives. Suitable additive include: fillers such as silica, talc, and the like; antioxidants (e.g., hindered phenolics such as IRGANOXTM 1010 or IRGANOXTM 1076 available from Ciba-Geigy); phosphites (e.g., IRGAFOSTM 168 available from Ciba-Geigy); anti-cling additives and anti-static additives; tackifiers, such as polybutenes, terpene resins, aliphatic and aromatic hydrocarbon resins, alkali metal and glycerol, stearates and hydrogenated rosins; UV stabilizers; heat stabilizers; release agents; anti-static agents; pigments; colorants; dyes; waxes; and the like.

[0052] Any blending required to make the compositions for the layers according to the present invention can be formed using conventional equipment and methods, such as by dry blending the individual components and subsequently

melt mixing in a mixer, or by mixing the components together directly in a mixer, such as a Banbury mixer, a Haake mixer, a Brabender internal mixer, or a single or twin-screw extruder including a compounding extruder and a side-arm extruder used directly downstream of a polymerization process or prior to film extrusion.

EXAMPLES

[0053] In the following examples, three-layer, A/B/A, films according to the invention and comparative films were produced on a commercially available extruder from Winmoller & Holscher. The co-extruded structures were symmetrical, having an inner core of 30 microns thick and two skins layers each 5 microns thick. Machine conditions were as follows: (a) die diameter: 250 mm; (b) die gap: 1.4 mm; (c) blow-up ratio: 3.0; (d) core extruder adapter temperature: 200°C; (e) skin extruder adapter temperature setting: 190°C; (f) die temperature: 200°C.

[0054] The various products used in the examples of Table 2 are identified below in Table 1:

TABLE 1

Product	Density	MI ³	Comments
¹ HYA800	0.961	0.7	HDPE Gas Phase
¹ HDZ222	0.964	2.4	Bimodal HDPE
¹ LL1201XV	0.9255	0.7	Ziegler-Natta LLDPE C ₄ Gas Phase
¹ Exceed 1327CA	0.927	1.3	Metallocene LLDPEC ₆ Gas Phase
¹ Exceed 1018CA	0.918	1.0	Metallocene LLDPE C ₆ Gas Phase
² EX489BA	0.9285	0.55	LDPE High Pressure
² EX514BA	0.9285	0.35	LDPE High Pressure

¹Commercially available from ExxonMobil

²Development versions. Improved versus commercially available as LD170BA.

³ASTM D-1238, condition E (2.16 kg load, 190 C)

[0051] Films having a thickness of 40 microns were formed using the compositions given in Table 2. Examples 2-3, 5-6, 8-9 are examples of the present invention having skin layers comprising mPE and HDPE, and core layers

comprising HDPE. Examples 11-12, 14-15, and 17-20 are examples of the present invention having skin layers comprising mPE but no HDPE, with the core layers comprising HDPE. The other examples are for comparative purposes. The results of various tests performed are shown in Table 3.

[0052] Haze is total haze measured according to ASTM D1003; Gloss 60° angle and Gloss 20° angle are both measured in accordance with ASTM D2457; Clarity is measured in accordance with ASTM D1746; the Elmendorf Tear values are both measured in accordance with ASTM D1922; Thermal Force values are both measured in accordance with ASTM D2838-95, set temperature: 190°C; relative 1% secant modulus and 10% offset yield are both measured in accordance with ASTM D882. Thermal force is measured based on ASTM D2838-95 procedure A using a Retramat tester supplied by Prodemat S.A.

Table 2

Str.	Thickness	Composition Skin Layers				Composition Middle Layer				Core extruder Melt pressure (Mpa)	Core extruder motor power (% of max)
		Ratio	Product	Ratio	Product	Ratio	Product	Ratio	Product		
1	40 µm	95%	1327CA	5%	HYA800	80%	EX489BA	20%	LL1201XV	327	32%
2	40 µm	95%	1327CA	5%	HYA800	80%	EX489BA	20%	HYA800	291	31%
3	40 µm	95%	1327CA	5%	HDZ222	80%	EX489BA	20%	HDZ222	273	33%
4	40 µm	95%	1327CA	5%	HYA800	70%	EX489BA	30%	LL1201XV	350	33%
5	40 µm	95%	1327CA	5%	HYA800	70%	EX489BA	30%	HYA800	292	30%
6	40 µm	95%	1327CA	5%	HDZ222	70%	EX489BA	30%	HDZ222	271	29%
7	40 µm	95%	1327CA	5%	HYA800	60%	EX489BA	40%	LL1201XV	367	35%
8	40 µm	95%	1327CA	5%	HYA800	60%	EX489BA	40%	HYA800	306	31%
9	40 µm	95%	1327CA	5%	HDZ222	60%	EX489BA	40%	HDZ222	271	29%
10	40 µm	85%	1327CA	15%	EX489BA	80%	EX489BA	20%	LL1201XV	332	32%
11	40 µm	85%	1327CA	15%	EX489BA	80%	EX489BA	20%	HYA800	291	30%
12	40 µm	85%	1327CA	15%	EX489BA	80%	EX489BA	20%	HDZ222	276	29%
13	40 µm	85%	1327CA	15%	EX489BA	70%	EX489BA	30%	LL1201XV	353	34%
14	40 µm	85%	1327CA	15%	EX489BA	70%	EX489BA	30%	HYA800	298	30%
15	40 µm	85%	1327CA	15%	EX489BA	70%	EX489BA	30%	HDZ222	275	30%
16	40 µm	85%	1327CA	15%	EX489BA	60%	EX489BA	40%	LL1201XV	367	35%
17	40 µm	85%	1327CA	15%	EX489BA	60%	EX489BA	40%	HYA800	304	32%
18	40 µm	85%	1327CA	15%	EX489BA	60%	EX489BA	40%	HDZ222	272	30%
19	40 µm	85%	1327CA	15%	EX514BA	70%	EX514BA	30%	HDZ222	294	32%
20	40 µm	85%	1018CA	15%	EX489BA	70%	EX489BA	30%	HDZ222	281	30%
22	40 µm	85%	LL1201XV	15%	EX489BA	70%	EX489BA	30%	LL1201XV	341	32%

Table 3

Run	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	22
Haze	9.6	5.6	5	9.6	6.2	6	10.9	7.5	6.8	4	4.4	4.4	4.5	4.9	5.1	4.8	5.9	5.8	5.20	4.90	5.20.
Gloss 60°	10	13	13.6	9.5	12.9	13.5	9.8	12.3	13.2	13.4	13.5	13.6	13.3	13.5	13.5	13.1	12.9	13.4	12.560.	13.540.	12.250.
Gloss 20°	5.4	11.5	13.5	5.9	10.5	12.8	6.5	10.4	12.5	12.6	11.4	13.2	12.6	12.7	13	11.7	10.3	12.8	10.70.	13.30.	10.30.
1% sec. mod. MD	339	449	429	340	493	492	338	547	564	334	380	409	329	444	471	327	488	539	426.0.	451.0.	322.0.
1% sec. mod TD	367	512	516	362	544	555	376	633	672	391	459	505	382	505	571	385	583	674	543.0.	517.0.	371.0.
Clarity	80	77	93	76	74	81	80	74	87	89	82	81	74	78	92	85	67	89	83.0	85.0.	83.0.
Elmendorf MD	5.9	14.2	9.3	4.3	10.2	9.1	2.3	4.7	0.9	5.5	7.1	13.4	4.6	11	10.6	9.8	3.6	2.3	15.440.	3.960.	5.560.
Elmendorf TD	6	7.3	7.9	8.3	9.1	9.9	10	12	12.5	6.6	1.4	8	7.7	10	9.5	5.6	11.9	11.9	7.910.	12.790.	7.520.
Thermal force MD N/15mm	1.07	1.26	1.31	1.04	1.4	1.55	0.98	1.74	1.76	1.01	1.3	1.42	0.99	1.49	1.54	1	1.57	1.69	1.673.	1.498.	1.0.
10% offset yield MD MPa	14.8	17.4	16.8	15.0	18.2	18.2	15.0	19.1	19.1	14.7	16.2	16.2	14.4	17.0	17.2	14.3	18.0	18.4	16.7	16.5	14.1
10% offset yield TD MPa	14.4	17.4	16.9	14.6	17.7	18.7	14.6	18.9	20.0	14.6	16.1	16.7	14.7	16.9	17.8	14.5	18.6	18.9	17.3	16.4	14.2

[0053] Several advantages can be seen in the present invention, according to the examples. For instance, melt pressure of the core extruder drop when the HDPE grades are used in the core as compared to the LLDPE grades (examples 2-3, 5-6, 8-9, 11-12, 14-15, 17-20 versus 1, 4, 7, 10, 13, 16, 22).

[0054] In the case of the skins comprising metallocene polyethylene and LDPE and the core comprising HDPE (examples 11-12, 14-15, 17-21), the 1% secant Modulus MD and TD values are significantly higher than the case where there is no HDPE in the core layer (examples 10, 13, 16, 22). Among other things, 1% secant Modulus provides a measure of the down-gauging possible using these films. The higher the 1% secant Modulus, the lower the gauge (thickness of the film) required to provide the same benefit. Increase in yield strength as measured by 10% offset yield is also a benefit which opens down-gauging possibilities. A thinner material having the same stiffness and strength (and thus lower cost) is highly sought after.

[0055] Likewise, skins comprised of blends of metallocene polyethylene and HDPE sandwiching a core comprising HDPE (examples 2-3, 5-6, and 8-9) had superior 1% secant Modulus relative to examples having cores not containing HDPE (examples 1, 4, and 7).

[0056] Furthermore, as is apparent from an inspection of the optical properties, the increase in strength and/or downgauging which accompanies the presence of HDPE in the core and/or skin is not significantly offset by loss of clarity or gloss values. Indeed it is particularly remarkable that Gloss at 20° and 60° are quite similar for examples according to the present invention, particularly with respect to the examples having HDPE both in the core and skins relative to the examples having HDPE in the skin but not the core. A small difference in Gloss 20° and 60° is important for display purposes, i.e., the angle of observance is not important. In Table 3, for instance, it can be seen that the difference in Gloss 20° and 60° values is about 0.1%, which is negligible. Typically for examples of the present invention differences of 2% are observed.

[0057] Moreover, examples according to the invention uniformly exhibit superior Elmendorf tear values (higher number being a measure of higher resistance to tearing) and higher thermal force (a measure of holding force when shrink

wrapped about collated items).

[0058] The invention has been described above with reference to numerous embodiments and specific examples. Many variations will suggest themselves to those skilled in this art in light of the above detailed description. All such obvious variations are within the full intended scope of the appended claims.

[0059] A preferred embodiment is a multilayer film structure having at least one first layer comprising HDPE and at least one second layer, different from said first layer, comprising a metallocene polyethylene; also more preferred embodiments, which may be combined where suitable, as would be recognized by one of skill in the art in possession of the present disclosure without undue experimentation: wherein said metallocene polyethylene is an mLLDPE; wherein said first layer further comprises LDPE in the amount of at least 50 wt.%, based on the composition of the first layer; wherein said second layer further comprises at least one additional polyolefin selected from group consisting of HDPE, LDPE, and mixtures thereof, in the amount of between 0.1 wt.% and 50 wt.%; wherein said first layer comprising HDPE is a core layer, said second layer comprising a metallocene polyethylene is a skin layer, and further comprising a second skin layer; wherein said first layer comprising HDPE is a core layer, said second layer comprising a metallocene polyethylene is a skin layer, and further comprising a second skin layer, said second skin layer comprising a metallocene polyethylene; wherein said first layer comprising HDPE is a core layer, said second layer comprising a metallocene polyethylene is a skin layer, and further comprising a second skin layer, said second skin layer comprising an mLLDPE; wherein said first layer comprising HDPE is a core layer, said second layer comprising a metallocene polyethylene is a skin layer, and further comprising a second skin layer, said second skin layer comprising an mLLDPE and further comprising at least one additional polyolefin selected from group consisting of HDPE, LDPE, and mixtures thereof, in the amount of between 0.1 wt.% and 50 wt.%; wherein said second skin comprises an mLLDPE and further comprises HDPE in the amount of between 0.1 wt.% and 50 wt.%; wherein none of the layers contain slip or antiblock additives; any of the three or more layer structures wherein the total thickness is 50 microns or less, preferably 40 microns or less, or even more

preferably wherein said first layer comprising HDPE has a thickness of about 40 microns or less, preferably 30 microns or less and each of said skin layers has a thickness of about 10 microns or less, preferably 5 microns or less.

[0060] Another preferred embodiment is a film comprising an A/B/A structure, wherein the A layers are skin layers, which may be the same or different, each independently are selected from a blend comprising an mPE having a density of between about 0.910 to 0.940 g/cm³, preferably 0.915 to 0.940 g/cm³, and optionally an HDPE, which if present, preferably has a density of between about 0.940 and 0.970 g/cm³, more preferably 0.955 to about 0.965 g/cm³, and most preferably from about 0.960 to about 0.965 g/cm³, and the B is a core layer comprising a blend comprising an HDPE, preferably having a density of between about 0.940 and 0.970 g/cm³, more preferably 0.955 to about 0.965 g/cm³, and most preferably from about 0.960 to about 0.965 g/cm³, and an LDPE, preferably having a density in the range of 0.916 to 0.935 g/cm³, more preferably 0.925 to 0.930 g/cm³; and also more preferred embodiments of this A/B/A structure, wherein core layer B comprise 60-90 wt.%, more preferably 70-80 wt.% LDPE, and 40-10 wt.% HDPE, more preferably 30-20 wt.%, and skin layers A are each independently selected from 80-100 wt.%, preferably 85-95 wt.% mPE, and 20-0 wt.% HDPE, more preferably 15-5 wt.%; and a more preferred embodiment of any of the above embodiments wherein said layers A and layer B, when formed into a coextruded structure A/B/A having a total thickness of less than 50 microns, has a 1% secant Modulus MD of at least 400 mPa, preferably 500 mPa, and a 1% secant Modulus TD of at least 400 mPa, preferably 500 mPa, and more preferably 600 mPa, the secant Modulus values measure in accordance with ASTM D882; and also any of the above embodiments wherein layers A and layer B, when formed into a coextruded structure A/B/A having a total thickness of less than 50 microns, has a difference in Gloss 20° and 60° of 2% or less, the Gloss values measured in accordance with ASTM D2457.

[0061] Additional preferred embodiments of any of the above would include the films having one or more of the performance parameters noted above in the experimental section, and would also include films having additional layers, such as A/B/C/D/E, wherein the skin layers A and E, which may be the same or

different, corresponding to the composition set forth above for skin layer A in the A/B/A structure, the composition C corresponds to the composition set forth above for core layer B in the A/B/A structure, and B and D, which may be the same or different, correspond to layers which may be selected from, without intending to be limiting, tie layers, reprocessed material layers and, in a preferred embodiment, additional layers having the composition corresponding to layer B in the A/B/A structure described previously.

[0062] Other preferred embodiments are coextruded films, heat shrinkable films, and collation shrink-wrapped structures according to any of the preceding embodiments (including preferred embodiments, more preferred embodiments, etc.).

[0063] Trade names used herein are indicated by a TM symbol or ® symbol, indicating that the names may be protected by certain trademark rights, e.g., they may be registered trademarks in various jurisdictions. All patents and patent applications, test procedures (such as ASTM methods, and the like), and other documents cited herein are fully incorporated by reference to the extent such disclosure is not inconsistent with this invention and for all jurisdictions in which such incorporation is permitted.